

Material

70 NBR 888

black

cross linking: sulfur

| | | | |
|-----------------------|----------------------|-------------|-------|
| revision index | revision date | page | 1 / 3 |
| 14 | 4/27/2022 | | |

| Physical properties | nominal range | typical values | |
|---|----------------------|-----------------------|-------------------|
| Density DIN EN ISO 1183-1 | 1.19 ±0.02 | 1.20 | g/cm ³ |
| Hardness DIN ISO 7619-1 | 70 ±5 | 68 | Shore |
| Micro hardness DIN ISO 48 Verfahren M | 70 +5/-8 | 68 | IRHD |
| Rebound resilience DIN 53512 | > 30 | 40 | % |
| Modulus 100 %, DIN 53504, S2 | > 3 | 4.5 | MPa |
| Tensile strength DIN 53504, S2 | > 12 | 15.2 | MPa |
| Elongation at break DIN 53504, S2 | > 250 | 280 | % |
| Compression set DIN ISO 815, 22 h, 100 °C | < 25 | 18 | % |
| Tear strength DIN 34-1, Methode B, Verfahren (b), 23 °C | --- | 12.5 | KN/m |
| Low Temperature DIN EN ISO 6721-2, (Torsionsschwingungsversuch) | --- | -49 | °C |
| Low Temperature DIN 53765, DSC | --- | -55 | °C |
| Temperature range | -50°C to 80°C | | |

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

| | | | | |
|--------------|----------------|-------------|--|----------------|
| | Country | Part | Remark | Expires |
| RoHS conform | | | including EU 2011/65 and EU2015/863 (ROHS III) | see DoC |

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance
Telefon: -
Fax: -
Email: MaterialCompliance@fst.com

Material
70 NBR 888

black

cross linking: sulfur

revision index

14

revision date

4/27/2022

page

2 / 3

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

Material 70 NBR 888

black

cross linking: sulfur

revision index

14

revision date

4/27/2022

page

3 / 3

Tested after ASTM D 2000: M 2 BF 714 B14 B34 EO14 EO34

| | | nominal range | typical values |
|---|-------|--------------------------|---------------------------|
| Hardness | Shore | 70 ±5 | 68 |
| Tensile strength | MPa | min. 14 | 15.1 |
| Elongation at break | % | min. 250 | 285 |
| B14 Compression set 22h/100°C | % | 25 | 8 |
| B34 Compression set 22h/100°C | % | 25 | 12 |
| EO14 Change after aging in IRM 901 70h/100°C | | | |
| Hardness | Shore | ±10 | 6 |
| Tensile strength | % | -25 | 10 |
| Elongation at break | % | -45 | -10 |
| Volume | % | ±10 | -9 |
| EO34 Change after aging in IRM 903 70h/100°C | | | |
| Hardness | Shore | -20 | -12 |
| Tensile strength | % | -45 | -5 |
| Elongation at break | % | -45 | -12 |
| Volume | % | 0 to 60 | 20 |

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com