

Material

70 EPDM 217676

blue

| | | | | |
|-------------------|-----------------------|----------------------|-------------|-----|
| print date | revision index | revision date | page | 1/1 |
| 1/14/2016 | 1 | 12/14/2015 | | |

| Physical properties | required | actual | |
|--|------------|--------|-------------------|
| Density DIN EN ISO 1183-1, 23 °C | 1.10 ±0.02 | 1.11 | g/cm ³ |
| Hardness DIN ISO 7619-1, Shore A, 23 °C | 70 ±5 | 71 | Shore |
| Tensile strength DIN 53504, S2, 23 °C | > 10 | 17.9 | MPa |
| Elongation at Break DIN 53504, S2, 23 °C | > 140 | 415 | % |
| Compression set DIN ISO 815, B, 24 h, 150 °C, 25 % | < 30 | 28 | % |

| Certificates | Country | Part | Remark | Expires | unlimited |
|--------------|---------|-------|-----------------|---------|-------------------------------------|
| FDA | USA | Seals | 21 CFR 177.2600 | | <input checked="" type="checkbox"/> |

Temperature-range: - 40 °C to 150 °C

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg
Global Material Technology

Wolfgang Becker

Phone: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com

