

Material

70 EPDM 391

black

cross linking: peroxidic

revision index	revision date	page	1 / 2
3	9/20/2011		

Physical properties	required	actual	
Density DIN EN ISO 1183-1, 23 °C	---	1.04	g/cm ³
Hardness DIN ISO 7619-1, Shore A, 23 °C	---	72	Shore
Modulus 100 %, DIN 53504, S2, 23 °C	---	---	MPa
Tensile strength DIN 53504, S2, 23 °C	---	16.8	MPa
Elongation at Break DIN 53504, S2, 23 °C	---	151	%
Compression set DIN ISO 815, B, 24 h, 150 °C, 25 %	---	13	%
Temperature range	-40°C to 150°C		

Certificates	Country	Part	Remark	Expires	unlimited
(EG) 1935/2004	EU		food		<input checked="" type="checkbox"/>
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)		<input checked="" type="checkbox"/>
ADI Free					<input checked="" type="checkbox"/>
FDA	USA	Seals	§ 177.2600		<input checked="" type="checkbox"/>
USP Chapter 87 (In vitro)	USA	Seals			<input checked="" type="checkbox"/>

Freudenberg
Freudenberg Sealing Technologies
Global Material Technology
Wolfgang Becker

Telefon: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com



Material 70 EPDM 391

black

cross linking: peroxidic

revision index

3

revision date

9/20/2011

page

2 / 2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg Sealing Technologies
Global Material Technology
Wolfgang Becker

Telefon: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com

