

Material 75 FKM 180497

black

cross linking: bisphenolically

Copolymer type 1, A

Print date	revision index	revision date	page	1/1
2/20/2020	11	11/5/2014		

Physical properties	nominal range	typical values	
Density DIN EN ISO 1183-1	2.06 ±0.03	2.07	g/cm ³
Hardness DIN ISO 7619-1	75 ±5	76	Shore
Micro hardness DIN ISO 48 Verfahren M	75 +5/-8	76	IRHD
Modulus 100 %, DIN 53504, S2	> 6.5	8.4	MPa
Tensile strength DIN 53504, S2	> 12	16.1	MPa
Elongation at break DIN 53504, S2	> 140	181	%
Compression set DIN ISO 815, 22 h, 175 °C	< 25	18	%
Low Temperature DIN 53765, DSC	---	-16	°C
Temperature range	-25°C to 200°C		

The material is resistant in water and water vapour to 150 °C.

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg
Freudenberg Sealing Technologies
Global Material Technology
Wolfgang Becker

Phone: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com



Material 75 FKM 180497

black

cross linking: bisphenolically

Copolymer type 1, A

Print date

2/20/2020

page 1/1

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
(EG) 1935/2004	EU		food		<input checked="" type="checkbox"/>
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)		<input checked="" type="checkbox"/>
3-A Sanitary	USA	Seals	Class I	12 / 2020	<input type="checkbox"/>
ADI Free			see certificate		<input checked="" type="checkbox"/>
Arrete 9.Nov 1994	F	Seals	food		<input checked="" type="checkbox"/>
BPA/Phthalate free			BPA/Phthalate free		<input checked="" type="checkbox"/>
FDA	USA	Seals	§ 177.2600		<input checked="" type="checkbox"/>
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		<input checked="" type="checkbox"/>
USP Chapter 87 (in vitro)	USA	Seals			<input checked="" type="checkbox"/>

Specific characteristic and limitations for the use in food contact are set out in the corresponding declaration of conformities.

Freudenberg

Freudenberg Sealing Technologies
Global Material Technology
Wolfgang Becker

Phone: +49 (0)6201/80-2893

Fax: +49 (0)6201/88-2893

Email: wolfgang.becker@FST.com