

## Material 75 Fluoroprene XP41

powder blue  
cross linking: peroxidic

<b>Print date</b>	<b>revision index</b>	<b>revision date</b>	<b>page</b>	1/1
2/7/2020	7	11/4/2019		

Physical properties	nominal range	typical values	
<b>Density</b> DIN EN ISO 1183-1, 23 °C	2.00 ±0.03	2.02	g/cm <sup>3</sup>
<b>Hardness</b> DIN ISO 7619-1, Shore A, 23 °C	75 ±5	77	Shore
<b>Modulus</b> 100 %, DIN 53504, S2, 23 °C	---	5.9	MPa
<b>Tensile strength</b> DIN 53504, S2, 23 °C	> 18	19.5	MPa
<b>Elongation at Break</b> DIN 53504, S2, 23 °C	> 250	306	%
<b>Compression set</b> DIN ISO 815, B, 24 h, 175 °C, 25 %	< 30	23	%
<b>Compression set</b> DIN ISO 815, B, 24 h, 150 °C, 25 %	---	19	%
<b>Compression set</b> DIN ISO 815, B, 70 h, 150 °C, 25 %	---	20	%
<b>Surface resistivity</b> DIN EN 62631-3-1 (VDE 0307-3-1) Ausgabe 2016, 50 %, 23 °C	---	5,1 E +11	Ohm
<b>Durchgangswiderstand</b> 500 V, 23 °C, 50 %	---	>1,0 E +13	Ohm*cm
<b>Temperature range</b>	-15°C to 200°C		

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

**Freudenberg**  
Freudenberg Sealing Technologies  
Global Material Technology  
Wolfgang Becker

Phone: +49 (0)6201/80-2893  
Fax: +49 (0)6201/88-2893  
Email: wolfgang.becker@FST.com



## Material 75 Fluoroprene XP41

powder blue  
cross linking: peroxidic

### Print date

2/7/2020

page 1/1

### Declarations of conformity

	Country	Part	Remark	Expires	unlimited
(EG) 1935/2004	EU		food		<input checked="" type="checkbox"/>
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)		<input checked="" type="checkbox"/>
3-A Sanitary	USA	Seals	Class I	12 / 2020	<input type="checkbox"/>
ADI Free			see certificate		<input checked="" type="checkbox"/>
Arrete 9.Nov 1994	F	Seals	food		<input checked="" type="checkbox"/>
BNIC (Cognac)	F	Seals			<input checked="" type="checkbox"/>
BPA/Phthalate free			BPA/Phthalate free		<input checked="" type="checkbox"/>
CMR Category 1A/1B free			see certificate		<input checked="" type="checkbox"/>
FDA	USA	Seals	§ 177.2600		<input checked="" type="checkbox"/>
Nano-free			see certificate		<input checked="" type="checkbox"/>
NSF 51	USA	Seals	food		<input checked="" type="checkbox"/>
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		<input checked="" type="checkbox"/>
USP Chapter 87 (In vitro)	USA	Seals			<input checked="" type="checkbox"/>
USP Class VI Ch. 88 - 121 °C	USA	Seals			<input checked="" type="checkbox"/>

Specific characteristic and limitations for the use in food contact are set out in the corresponding declaration of conformities.

### Freudenberg

Freudenberg Sealing Technologies  
Global Material Technology  
Wolfgang Becker

Phone: +49 (0)6201/80-2893  
Fax: +49 (0)6201/88-2893  
Email: wolfgang.becker@FST.com