

Material

70 FKM 37508

auburn

cross linking: bisphenolically

= V178

75 +- 5 Shore A (at the test slab)

revision index revision date
20 3/30/2022

page 1 / 2

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1, 23 °C	1.99 ±0.03	1.99	g/cm³
Hardness DIN ISO 7619-1, Shore A, 23 °C	75 ±5	76	Shore
Micro hardness DIN ISO 48	75 +5/-8	73	IRHD
Tensile strength DIN 53504, S2, 23 °C	> 11.5	15.7	MPa
Elongation at break DIN 53504, S2, 23 °C	> 130	160	%
Compression set DIN ISO 815, Slab B, 24 h, 200 °C, 25 %	< 15	9	%
Low Temperature DIN 53765, DSC	---	-16	°C
Temperature range	-20°C to 200°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
(EG) 1935/2004	EU		food	see DoC
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)	see DoC
ADI Free			see certificate	see DoC
BPA/Phthalate free			BPA/Phthalate free	see DoC
FDA	USA	Seals	\$ 177.2600	see DoC
Info ROHS and ELV			EU 2000/53 (ELV) including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -
Fax: -
Email: MaterialCompliance@fst.com



Material

70 FKM 37508

auburn

cross linking: bisphenolically

= V178

75 +- 5 Shore A (at the test slab)

revision index

20

revision date

3/30/2022

page 2 / 2

No ASTM D2000 properties available

Attention! The debit of the micro-hardness at the o-ring is defined at 70+5/-8 IRHD

Assay according to DIN IEC 93/VDE 303 part 30:

contact resistance > 10⁹ Ohm

surface resistance > 10⁹ Ohm

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactory process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Attention! The production of this compound is suspended. Please contact us.

Freudenberg

Freudenberg FST GmbH
Technology&Innovation
Material Compliance

Telefon: -

Fax: -

Email: MaterialCompliance@fst.com

