

Material 75 FKM 38133

green

cross linking: bisphenolically

revision index 3	revision date 2/10/2023			page	1/2
Physical properties		nominal ra	nge	typical values	
Density ASTM D297, 23 °C		2.35 ±0	0.03	2.35	g/cm³
Hardness ASTM D2240, Shore A, 23 °C		75	5 ±5	75	Shore
Tensile strength DIN 53504, S2, 23 °C			> 9	9	MPa
Elongation at break DIN 53504, S2, 23 °C		>	200	230	%
Tear strength ASTM D624, B, 23 °C		>	> 20	24	KN/m
Compression set ASTM D395, Slab B, 22 h, 200	°C, 25 %	•	< 15	10	%
Temperature range		-20°C to 200°C			

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
(EG) 2023/2006 (GMP)	EU		(EG) 2023/2006 (GMP)	see DoC
FDA	USA	Seals	§ 177.2600	see DoC
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Freudenberg

Freudenberg FST GmbH Technology&Innovation Material Compliance

Telefon: -Fax: -

Email: MaterialCompliance@fst.com





Material 75 FKM 38133

green

cross linking: bisphenolically

revision index revision date

3 2/10/2023 page 2/2

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg

Freudenberg FST GmbH Technology&Innovation Material Compliance

Telefon: -Fax: -

Email: MaterialCompliance@fst.com